



## TECHNICAL DETASHEET

### Grade - DELORO 222 (CHINA CLAY)

#### Characteristics

#### Standard Specifications

##### Physical Properties

Brightness (ISO) %	95 ± 1
Yellowness (YI) %	2-3
Bulk Density (KG/LIT)	0.275 -0.300
Oil Absorption	60 - 65
Moisture (W/W)%	< 0.5
pH (of 10 % suspension)	5.0 - 7.0

##### PSD on Sedigraph III V1.04

Particle Size < 2 $\mu$	75 ± 1 %
d(50) $\mu$ (W/W)%	0.9 to 1.1

##### Sieve Residue

Retention % on 500 # ASTM sieve	< 0.01
---------------------------------	--------



#### Chemical Composition

SiO <sub>2</sub> %	52-54
Al <sub>2</sub> O <sub>3</sub> %	42-44
Fe <sub>2</sub> O <sub>3</sub> %	< 0.5
Loss on Ignition	0.5

The figures given in the data sheet are mean representative values. Due to minerals being natural product, the specification in this data sheet may not be treated as warranty.

 +91 90992 70714

 [info@deltacorporation.in](mailto:info@deltacorporation.in)

 Plot No-133, Laloda, Laloda,  
Sabarkantha, Gujarat, 383430