

## PRODUCT: DELCRO QUARTZ 60

### PHYSICAL ANALYSIS

Residue on 240 Mesh Sieve	Max. 1.0 %
Dry Brightness	Min. 91.0 %
Tapped Bulk Density	1350 –1450 Gm / Lit
Oil Absorption	14.0 – 18.0 Gm/100Gm
Specific Gravity	2.7
pH Of Sat. Solution	7.0 – 8.0
Moisture Content	Max. 0.5 %

### **CHEMICAL ANALYSIS**

<b>SiO<sub>2</sub></b>	Min. 98.0 %
<b>Fe<sub>2</sub>O<sub>3</sub></b>	Max 1.0 %
<b>Al<sub>2</sub>O<sub>3</sub></b>	Max. 0.5 %
<b>Loss On Ignition</b>	0.35 %

 +91 90992 70714

 [info@deltacorporation.in](mailto:info@deltacorporation.in)

 Plot No-133, Laloda, Laloda,  
Sabarkantha, Gujarat, 383430